

# Z221

## FKM 80 BROWN

### RAL 8028

REV. 2

#### General Application

#### Temperature Range

From -20°C  
To 220°C

#### General Environmental Application

Chemicals  
Hydrocarbons  
High Temperatures  
---  
---

#### Compliances

#### Note

...

#### Disclaimer

Tests performed on test slabs. Temperatures, applications and indications are meant as basic suggestions and valid for static applications with no other specific media and or conditions.

#### PHYSICAL AND MECHANICAL PROPERTIES

Property	Test STD	Unit	Value
Density	ASTM D297	g/cm <sup>3</sup>	2,23 ± 0,03
Hardness	ASTM D2240	ShA	80 ±5
Tensile Strength	ASTM D412	N/mm <sup>2</sup>	>10
Elongation	ASTM D412	%	>135
Tear resistance	ASTM D624B	N/mm	>25
TR 10	ASTM D1329	°C	<-17
Brittle Point		°C	<
C. Set 24h @200°C	ASTM D395B	%	<14
C. Set 70h @200°C	ASTM D395B	%	<24

#### AGEING PROPERTIES

Environment	Test STD	Unit	Value
	<i>Hardness Change</i>	ShA	
	<i>Tensile Strength</i>	%	
	<i>Elongation</i>	%	
	<i>Volume</i>	%	
	<i>Weight</i>	%	
Air 70h @250°C	ASTM D573		
	<i>Hardness Change</i>	ShA	+3
	<i>Tensile Strength</i>	%	-10,5
	<i>Elongation</i>	%	-12,3
	<i>Volume</i>	%	
	<i>Weight</i>	%	
Oil ASTM 3 70h @150°C	ASTM D471		
	<i>Hardness Change</i>	ShA	-1,5
	<i>Tensile Strength</i>	%	-9
	<i>Elongation</i>	%	-5
	<i>Volume</i>	%	+2,3
	<i>Weight</i>	%	
Fuel ASTM C 70h @23°C	ASTM D471		
	<i>Hardness Change</i>	ShA	-4
	<i>Tensile Strength</i>	%	-17
	<i>Elongation</i>	%	-15,5
	<i>Volume</i>	%	+4,4
	<i>Weight</i>	%	

