

# Z227

## FKM 75 RED

## RAL 3016

REV. 2

### General Application

#### Temperature Range

From -20°C  
To 220°C

### General Environmental Application

Chemicals  
Hydrocarbons  
High Temperatures  
---  
---

### Compliances

### Note

...

### Disclaimer

Tests performed on test slabs. Temperatures, applications and indications are meant as basic suggestions and valid for static applications with no other specific media and or conditions.

### PHYSICAL AND MECHANICAL PROPERTIES

Property	Test STD	Unit	Value
Density	ASTM D297	g/cm <sup>3</sup>	2,04 ± 0,03
Hardness	ASTM D2240	ShA	75 ±5
Tensile Strength	ASTM D412	N/mm <sup>2</sup>	>11
Elongation	ASTM D412	%	>160
Tear resistance	ASTM D624B	N/mm	>29
TR 10	ASTM D1329	°C	<-17
Brittle Point		°C	<
C. Set 24h @200°C	ASTM D395B	%	<14
C. Set 70h @200°C	ASTM D395B	%	<22

### AGEING PROPERTIES

Environment	Test STD	Unit	Value
	<i>Hardness Change</i>	ShA	
	<i>Tensile Strength</i>	%	
	<i>Elongation</i>	%	
	<i>Volume</i>	%	
	<i>Weight</i>	%	
Air 70h @250°C	ASTM D573		
	<i>Hardness Change</i>	ShA	+3
	<i>Tensile Strength</i>	%	-11,6
	<i>Elongation</i>	%	-15,5
	<i>Volume</i>	%	
	<i>Weight</i>	%	
	<i>Hardness Change</i>	ShA	
	<i>Tensile Strength</i>	%	
	<i>Elongation</i>	%	
	<i>Volume</i>	%	
	<i>Weight</i>	%	
	<i>Hardness Change</i>	ShA	
	<i>Tensile Strength</i>	%	
	<i>Elongation</i>	%	
	<i>Volume</i>	%	
	<i>Weight</i>	%	

